

BLH**980 - 1050 °C**

Pearl White and smooth crockery with great plasticity. Excellent drying behavior, also with glazes and underglazes. Ideal for turning, press, modeling

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	4,25%	1020°C	16,71%	19,00%	1,30%

Thermal coefficient

80x10⁻⁷°C⁻¹ (48.1-500°C)