


CBP

980 - 1050 °C



Terracotta earthenware body. Pink/beige depending on the temperature and atmosphere of the oven.
Intended for artistic, table, and decorative ceramics.
Ideal for turning and modeling.

Technical data sheet

Drying		Firing			
Humidity	Shrinkage	°C	l. weight	Water Absorption	Contracción
22%	6,90%	950		21,00%	0,28%
		1000		14,50%	0,28%
		1100		13,00%	0,35%

Thermal coefficient

72.1x10⁻⁷°C⁻¹ (25-500°C)