



## **Red earthenware. FE**

Good plasticity equally suitable for throwing as well handbuilding and machine making. Ideal for "Terre vernissée" technic.

Firing temperature: 970-1050°C (1178-1922°F)

FE clay is suitable for all handbuilding methods of modeling and wheel throwing.

Its extreme plasticity makes even very large pieces easier to throw.

Single or dual cooking

Shrinkage dry 5.50%

Shrinkage 1000°C (1832°F) 1%

Porosity 1000°C (1832°F) 16.50%

Coef dilatation 20-500°C (68-932°F) 84

